

TECH DATA SHEET

1. PRODUCT NAME

Touch 'n Seal[®] Quick Cure HY (High Yield) Polyurethane Foam Sealant

Touch 'n Seal[®] Quick Cure RX (Reduced Expansion) Polyurethane Foam Sealant

2. MANUFACTURER

 Convenience Products

 866 Horan Dr., Fenton, MO 63026 USA

 (636) 349-5855

 (800) 325-6180

 FAX
 (636) 349-5335

 E-mail
 support@touch-n-seal.com

 Website:
 www.touch-n-seal.com

3. PRODUCT DESCRIPTION

Touch 'n Seal Quick Cure foams are high performance, single component, moisture curing, Class 1 fire retardant, expanding polyurethane sealants. Quick Cure sealants are available in both straw dispensed aerosol cans and larger cylinders with hoses and applicators.

Quick Cure sealants are available in High Yield (HY) and Reduced Expansion (RX) formulations. Use Quick Cure HY when high expansion is needed to fill and seal larger gaps and cracks. Use Quick Cure RX when requiring controlled dispensing rate and less post expansion. Both formulations are tack free in 30 minutes or less, can be trimmed in 1 hour and are fully cured in about 24 hours, depending upon humidity and temperature.

Basic Use

Use Quick Cure Polyurethane Foam Sealants to permanently air seal and insulate gaps and cracks to block drafts, moisture and insects while improving comfort and reducing energy usage in commercial, industrial, agricultural and residential applications. Use to seal around plumbing, ventilation outlets, electrical junctions, between sill plates and concrete slabs, or anywhere you need a fast, economical air-sealing moisture barrier.

For fireblock and sealing applications refer to ICC-ES ESR 1926 detail.

Quick Cure foams provide permanent insulating and air sealing solutions to building component materials including wood, masonry, insulating foam boards, metal, wire insulation, plastics and sheetrock.

Use Touch 'n Seal Poly-Clean Foam Cleaner to clean wet Quick Cure foams from hands, tools and foam applicator guns.

Composition & Materials

Touch 'n Seal Quick Cure polyurethane onecomponent expanding foam sealants are permanent, hypoallergenic and dry within minutes of application. Quick Cure foams are non-toxic and will not decompose with age.

Sizes

HY Straw Foam - Item # 4004521212 12 ounce (340 gm)



Convenience Products

866 Horan Drive, Fenton, MO 63026 USA (800) 325-6180, (636) 349-5855 Tel. HY Straw Foam - Item # 4004521224 24 ounce (680 gm)

HY Foam Complete - Item # 4004518100 10 pounds (4.54 kg)

HY Foam Complete - Item # 4004518160 16 pounds (7.26 kg)

RX Foam Complete - Item # 4004510950 10 pounds (4.54 kg)

RX Foam Complete - Item # 4004516900 16 pounds (7.26 kg)

Features/Benefits

- Multiple package sizes
- Easy to use
- · Class 1 fire retardant
- Provides a permanent seal against air, moisture and insect infiltration
- Easier to use than caulk type penetration sealants
- Bonds to common building materials including wood, concrete, insulating foam boards, metal, plastics and sheetrock
- Available in both straw and cylinder dispensing systems
- Reduces energy loss
- No ozone depleting chemicals
- Does not shrink
- Does not trap moisture, dust and allergens as does fiberglass insulation
- Expands to fill gaps and cracks, reducing air exchanges
- Reduces use of fossil fuels and improves air quality
- Helps to reduce Greenhouse Gas Emissions
- Closed cell structure

Limitations

- Foam is combustible. Do not expose to temperatures above 240°F (116°C), open flames or sparks
- Not for exposure to ultraviolet light
- Chemicals must be 50°-100°F (10°-38°C) prior to application
- Do not store in temperatures above 120°F (49°C)
- Always refer to local building code regulations
 Do not leave product exposed; cover with approved facings
- Propellant in 12 & 24 ounce straw foam is flammable; read MSDS and do not use near high heat, sparks or open flame
- Not a fire stop material

4. TECHNICAL DATA

Applicable Standards

- ASTM E-84 Surface Burning Characteristics
- ASTM E-96 Water Vapor Transmission
- ASTM C-273 Shear Strength
- ASTM C-273 Shear Strain
- ASTM C-518 R-Value
- ASTM E-814 Modified for Fire Block
- ASTM C-1536 Yield
- ASTM D-1621 Compressive Strength
- ASTM D-1622 Core Density



- ASTM D-1623 Tensile Strength
- ASTM D-6226 Closed Cell Content
- UL 1715 Fire Test

Approvals/Certifications/Listings

- ICC ES ESR-1926
- International Building Code
- International Residential Code
- BOCA National Building Code
- 1999 Standard Building Code
- California Bureau of Home Furnishings and Insulation
- Underwriters Laboratories Classified Caulking & Sealants

Shelf Life

12 months in unopened container when stored between 60° - $90^{\circ}F$ (16° - $32^{\circ}C$), in a dry, well-ventilated area.

Storage & Disposal

Keep containers tightly closed in a cool, wellventilated area. Ideal storage temperature is 60°-90°F (16°-32°C). Storage above 90°F (32°C) will reduce shelf life. Do not store at temperatures greater than 120°F (49°C). Avoid freezing. Do not expose containers to conditions that may damage, puncture, or burst the containers. Dispose of leftover material/containers in accordance with Federal, state and local regulations. See Material Safety Data Sheet for more information.

5. INSTALLATION/APPLICATION

Always refer to local building codes prior to application of Touch 'n Seal foam sealants.

The Touch 'n Seal[®] Quick Cure one-component expanding foam sealant can be applied to and will adhere to almost any traditional construct surfaces including wood, masonry, insulating foam boards, metal, plastics and sheetrock.

Surfaces to receive Touch 'n Seal foam sealants must be dry, clean and free of dust, dirt, grease and other substances that may inhibit proper adhesion. For best results apply Touch 'n Seal[®] Quick Cure expanding foam sealant when surface and ambient temperatures are between 60°-100°F (16°-38°C). Temperature of chemical contents must be between 50°F-100°F (10°C-38°C) before dispensing.

Use all chemical contents within 30 days of initial dispensing.

Keep out of reach of children. Always wear proper personal protective equipment, including





TECH DATA SHEET

gloves, clothing and eyewear. Use in wellventilated area.

Please refer to manufacturer's instructions or request a faxed set of instructions from Convenience Products by calling Customer Service at 800-325-6180. 6. AVAILABILITY & COST

Availability

Touch 'n Seal polyurethane foams are available throughout the U.S., Canada, Mexico and the world. Contact Convenience Products Customer Service at 800-325-6180 or FAX 636-349-1708 for distributor information.

Cost

Contact Convenience Products for local distributors who can provide cost and delivery information.

7. WARRANTY

Convenience Products warrants its Touch 'n Seal Convenience Products. products to be free of defects in workmanship and function.

Convenience Products is not liable for any incidental, consequential or any other damages beyond the description herein, however, certain states have specific laws regarding limitation on incidental or consequential damages, in which case, and you may have other legal rights. 8. MAINTÉNANCÉ

None

9. TECHNICAL SERVICES

Technical assistance, including more detailed information, product literature, test results, assistance with preparing project specifications and application training is available by contacting

10. FILING SYSTEMS

Additional information is available from the manufacturer upon request.

The information contained herein was accurate at the time of publishing. Please refer to the Touch 'N Seal website for the latest information.

TYPICAL PROPERTIE	S OF TOUCH 'N SEAL QUIC	CK CURE POLYUF	RETHANE CLASS 1 FOAM SEALANT
Container Sizes	12 & 24 ounce (340 & 680 gm) Straw Foam		10 & 16 pound (4.54 & 7.26 kg) Cylinder Foam
Shelf Life	1 year; unopened container		1 year; unopened container
Surface Dry Time/Surface Tack Free Time	< 30 minutes @ 72°F/ 50% R.H.		< 15 minutes @ 72°F/50% R.H.
Fully Cured	24 hours @ 72°F/ 50% R.H.		24 hours @ 72°F/ 50% R.H.
Trimmable	< 1 hour @ 72°F/ 50% R.H.		< 1 hour @ 72°F/ 50% R.H.
ASTM E-84 Surface Burning Characteristics			
Flame Spread	10		20
Smoke Development	15		25
ASTM E-96 Water Vapor Transmission	10 perm inches (25mm)		3.3 perm inch
ASTM C-273 Shear Strength	N/A		18 psi (1.27 kg/cm ²)
ASTM C-273 Shear Strain	N/A		57%
ASTM C-518 R-Value	4 - 5 /in. (25 mm)		4 - 5 /in. (25 mm)
ASTM E-814 Modified for Fire Block	Pass		Pass
ASTM C-1536 Yield	12 oz (340gm) ¼ in. (6.4mm) dia. bead – 900 ft. (280m) 3/8 in. (9.5mm) dia. bead – 400 ft. (124m)		10 lb HY ¼ in. (6.4mm) dia. bead – 15,300 ft. (4,663m) <u>3/8 in. (9.5mm) dia. bead – 6,800 ft. (2,072m)</u> 16 lb HY ¼ in. (6.4mm) dia. bead – 24,400 ft. (7,437m) <u>3/8 in. (9.5mm) dia. bead – 10,900 ft. (3,322m)</u>
	24 oz (680gm) ¼ in. (6.4mm) dia. bead – 1,800 ft. (550m) 3/8 in. (9.5mm) dia. bead – 800 ft. (249m)		10 lb RX ¼ in. (6.4mm) dia. bead – 14,700 ft. (4,480m) <u>3/8 in. (9.5mm) dia. bead – 6,500 ft. (1,981m)</u> 16 lb RX ¼ in. (6.4mm) dia. bead – 24,080 ft. (7,340m) <u>3/8 in. (9.5mm) dia. bead – 10,500 ft. (3,200m)</u>
ASTM D-1621 Compressive Strength			11 psi (0.77 kg/cm ²)
ASTM D-1622 Core Density	1.75 +/25 pcf (20.8 +/1 4.0 kg/m ³)		1.3 – 1.8 pcf (20.8 – 28.8 kg/m ³)
ASTM D-1623 Tensile Strength Percent elongation at break	N/A		33 psi (0.02 kg/cm ²) 10%
UL 1715 Corner Room Fire Test	N/A		Pass - No thermal barrier required in Type V construction
ASTM D-6226 Closed Cell Content	N/A		70%
International Building Code	Conforms		Conforms
International Residential Code	Conforms		Conforms
BOCA National Building	Conforms		Conforms
1999 Standard Building Code	Conforms		Conforms
ICC-ES	ESR-1926		ESR-1926
California Bureau of Home Furnishings and Insulation	Listed		Listed
NPFA 30B Classification	Aerosol Level 2		N/A
Underwriters Laboratories Classified Caulking & Sealants	UL ULC R14175 BLEZC.R14175		R14175



