



HIGH TEMPERATURE BLANKET

Temperature Limit: 1000° F (538° C)

DESCRIPTION

High Temperature Board is a lightweight insulation blanket (1.1 PCF, 17.6 kg/m³) made from highly resilient, inorganic glass fibers bonded with a high-temperature thermosetting resin.

APPLICATION

Manson Insulation High Temperature Blanket is used for industrial heating equipment up to 1000° F (538° C), such as industrial furnaces, panel systems, marine applications and irregular surfaces.

FEATURES AND BENEFITS

GREENGUARD Certification

- Recycled glass content verified every six months by UL Environment

EUCEB

- Tested and certified to meet EUCEB requirements

Excellent Thermal Properties

- Low thermal conductivity ratings to 1000° F (538° C)

Low Installed Cost

- Lightweight and easy to handle and fabricate
- Flexibility make them ideal for flat or irregular surfaces

Packaging - Cartons & Sleeves

- Tough and resilient
- Resists damage in shipment, during and after installation

SPECIFICATION COMPLIANCE

- ASTM C1139 replaces MIL-I-22023D
- HH-1-558C
- Form B, Class 7,8
- City of New York MEA 364-83-M

- ASTM C795
 - MIL-I-24244
 - NRC Reg. Guide 1.36
- (Certification needs to be specified at the time of the order)

CAUTION

Glass mineral wool may cause temporary skin irritation. Wear long-sleeved, loose-fitting clothing, head covering, gloves and eye protection when handling and applying material. Wash with soap and warm water after handling. Wash work clothes separately and rinse washer. A disposable mask designed for nuisance type dusts should be used where sensitivity to dust and airborne particles may cause irritation to the nose or throat.

GLASS MINERAL WOOL AND MOLD

Glass mineral wool insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold, it must be discarded. If the material is wet but shows no evidence of mold, it should be dried rapidly and thoroughly. If it shows signs of facing degradation from wetting, it should be replaced.

NOTES

The chemical and physical properties of Manson Insulation High Temperature Blanket represent average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

Check with your Manson Insulation Area Manager to ensure information is current.

HIGH TEMPERATURE BLANKET

Temperature Limit: 1000° F (538° C)

APPLICATION & SPECIFICATION GUIDELINES

Precaution

- During initial heat-up to operating temperatures above 350° F (177° C), a slight odor and some smoke may be given off as a portion of the bonding material used in the insulation begins to undergo a controlled decomposition.
- If natural convection is not adequate in confined areas, forced ventilation should be provided in order to protect against any harmful fumes and vapors that might be generated.

Storage

- Protect material from water damage or other abuse. Protect from welding sparks and open flame. The material may be stored outside if the packaging is not damaged.

Preparation


- Apply the product on clean, dry surfaces.

Application

- There is no heat-up cycle requires for Manson Insulation High Temperature Blanket.
- The product should be secured with welded pins or studs and covered with sheet metal. An alternate method entails covering the insulation with a metal mesh and insulating cement, canvassing and painting.
- Care should be taken to avoid over compressing the insulation with the retaining washer.
- Pins and studs shall be located a maximum of 4" (102 mm) from each edge and spaced no greater than 16" (406 mm) on center.
- For application of Manson High Temperature Blanket over 500° F (260° C), double layer application is recommended with staggered joints.

TECHNICAL DATA		
PROPERTY (UNIT)	TEST	PERFORMANCE
Corrosiveness	ASTM C665	Does not accelerate corrosion of steel
Maximum Service Temperature	ASTM C411	1000° F (538° C)
Water Vapor Sorption (by volume)	ASTM C1104	0.1% or less
Alkalinity	ASTM C871	Less than 0.6% as Na ₂ O, pH between 7.5 and 12.0
Mold Growth	ASTM C1338	Pass
Surface Burning Characteristics (flame spread/smoke developed)	ASTM E84, UL 723, CAN/ULC S102-M88	25/50

FORMS AVAILABLE		
THICKNESS	WIDTH	LENGTH
1" (25 mm)	48" (1,219 mm)	75' (22.9 m)
1½" (38 mm)		50' (15.2 m)
2" (51 mm)		75' (22.9 m)
2½" (64 mm)		60' (18.3 m)
3" (76 mm)		50' (15.2 m)
3½" (89 mm)		45' (13.7 m)
4" (102 mm)		40' (12.2 m)



MEAN TEMPERATURE	K	K(SI)
100° F (38° C)	0.28	0.040
200° F (93° C)	0.38	0.055
300° F (149° C)	0.52	0.075
400° F (204° C)	0.70	0.101
500° F (260° C)	0.90	0.130



Manson Insulation

One Knauf Drive
Shelbyville, IN, USA 46176
(800) 825-4434

www.imanson.com