



PHILLYCLAD 5066A – TECHNICAL BULLETIN #659F

Revised: 01/2017

PRODUCT DESCRIPTION

PHILLYCLAD 5066A is a two component, heavy duty coating designed for applications requiring a high degree of resiliency combined with excellent adhesion and impact properties. The compound is resistant to oils, fuels and most chemicals, is nontoxic and contains no volatiles. PHILLYCLAD 5066A is selfextinguishing and meets the requirements of ASTM-D-635.

USE & BENEFITS

Typical applications include the coating of lagging or insulation on piping, boilers, valves, etc., to prevent the absorption of oils and the associated fire hazard. PHILLYCLAD 5066A is designed to protect monolithic types of insulation and other semiresilient substrates from abuse or damage. Easily applied at thicknesses up to 6mm (1/4"), PHILLYCLAD 5066A effectively seals out contaminants while providing a tough resilient coating highly resistant to heat, impact or other damage.


APPLICATION INSTRUCTIONS

PHILLYCLAD 5066A is generally applied by trowel or putty knife at thicknesses to 6mm (1/4"). Maximum adhesion is achieved where surfaces have been cleaned of all dust, oils, old coatings, etc. Metal surfaces should be thoroughly degreased to insure proper adhesion. Following application, PHILLYCLAD 5066A can be smoothed and neatly faired

with hand and clean water. Caulking around header joints, handholes, heat riser, burner receiver, etc., with silicone caulking compound will further insure against oil penetration. Apply PHILLYCLAD 5066A over caulking compound.

MIXING INSTRUCTIONS

Mix one part black hardener with one part white resin by volume. Mix on flat surface with trowel or putty knife until a uniform streak-free gray color is achieved. Warming material to 21°C (70°F) or above will facilitate ease of mixing and application.



PHILLYCLAD 5066A

PROTECTIVE COATING AND SEALANT
FOR INSULATION OR LAGGING

PHYSICAL PROPERTIES

COLOR	Resin - White Hardener - Black Mixed - Dark Gray
COVERAGE	0.6m ² /liter @6mm (6.4 sq.ft./gallon@ 1/4")
CURE TIME	Overnight at 21°C (70°F) 4 hours or less on hot surface
FIRE RESISTANCE	Self extinguishing
PACKAGING	7.6 liter (2 gallon) Kit (5066A) 1.9 liter (2 quart) Kit (5066B) 37.8 liter (10 gallon) Kit (5066C)
POT LIFE	4 hours @21°C (70°F)
SHELF LIFE	Two years
SOLVENT CLEANER	IMPAX IXT-59
VISCOSITY	Mastic Paste

General: Every reasonable effort is made to insure the technical information and recommendations on these data pages are true and accurate to the best of our knowledge at the date of issuance. However, this information is subject to change without notice. Prior versions of this publication are invalid with the release of this version. Products and information are intended for use by qualified applicators that have the required background, technical knowledge, and equipment to perform said tasks in a satisfactory manner. Consult your local distributor for product availability, additional product information, and technical support. **Warranty:** ITW Engineered Polymers, a division of Illinois Tool Works Inc., warrants that its products meet their printed specifications. This is the sole warranty. This warranty expires one year after product shipment. **Warranty Claims:** If any product fails to meet the above, ITW Engineered Polymers will, at its option, either replace the product or refund the purchase price. ITW Engineered Polymers will have no other liability for breach of warranty, negligence, or otherwise. All warranty claims must be made in writing within one year of the date of shipment. No other claims will be considered. **Disclaimer:** ITW Engineered Polymers makes no other warranty, expressed or implied, and specifically disclaims any warranty of merchantability or fitness for a particular purpose. Suggestions concerning the use of products are not warranties. The purchaser assumes the responsibility for determining suitability of products and appropriate use. ITW Engineered Polymers' sole liability, for breach of warranty, negligence or otherwise, shall be the replacement of product or refund of the purchase price, at ITW Engineered Polymers' election. Under no circumstances shall ITW Engineered Polymers be liable for any indirect, incidental or consequential damages. **Modification of Warranty:** No distributor or sales representative has the authority to change the above provisions. No change in the above provisions will be valid unless in writing and signed by an officer or the Technical Director of ITW Engineered Polymers. No term of any purchase order shall serve to modify any provision of this document. **Mediation and Arbitration:** If any dispute arises relating to products or product warranties, either the purchaser or ITW Engineered Polymers may a) initiate mediation under the then current Center for Public Resources (CPR) Model Procedure for Mediation of Business Disputes, or b) initiate a non-binding arbitration under the rules of the American Arbitration Association for the resolution of commercial disputes.