

Sikaflex® Textured Sealant

One-component, all purpose, polyurethane sealant

Description	Sikaflex Textured Sealant is a moisture-cured, 1-component, polyurethane-based, non-sag elastomeric sealant capable of $\pm 25\%$ joint movement. Meets Federal specification TT-S-00230C, Type II Class A. Meets ASTM C-920, Type S, Grade NS, Class 25.
Where to Use	<ul style="list-style-type: none"> ■ Designed for all types of joints where maximum depth of sealant will not exceed 1/2 inch. ■ Suitable for vertical and horizontal joints; readily placeable at 40°F (4°C). ■ Has many applications as an elastic sealant between materials with dissimilar coefficients of expansion. ■ Ideal for: <ul style="list-style-type: none"> ◆ Weatherproofing of joints between brickwork, blockwork, masonry, wood and concrete or metal frames. ◆ Joints in walls, balconies, around window or door frames. ◆ Expansion joints.
Advantages	<ul style="list-style-type: none"> ■ Excellent adhesion – bonds to most construction materials without a primer. ■ Textured appearance blends well to rough or stucco type surfaces. ■ Hides imperfections from tooling that a smooth sealant does not. ■ Excellent resistance to aging, weathering. ■ Non-staining. ■ Paintable with water-, oil- and rubber-based paints. ■ High elasticity – cures to a tough, durable, flexible consistency with exceptional cut and tear-resistance. ■ Stress relaxation. ■ Urethane-based; suggested by EPA for radon reduction.
Packaging	Disposable 10.1 fl. oz., moisture-proof composite cartridges, 24/case.

Typical Data (Material and curing conditions @ 73°F (23°C) and 50% R.H.)

RESULTS MAY DIFFER BASED UPON STATISTICAL VARIATIONS DEPENDING UPON MIXING METHODS AND EQUIPMENT, TEMPERATURE, APPLICATION METHODS, TEST METHODS, ACTUAL SITE CONDITIONS AND CURING CONDITIONS.

Shelf Life	12 months
Storage Conditions	Store at 40°-95°F (4°-35°C). Condition material to 65°-75°F (18°-24°C) before using.
VOC Content	40 g/L
Standard Colors	White, aluminum gray, limestone, dark bronze, buff and stone.
Application Temperature	40° to 100°F (4°-38°C) . Sealant should be installed when joint is at midrange of its anticipated movement.
Service Range	-40° to 170°F (-40°-77°C)
Curing Rate	Tack-free time: <6 hrs. Final cure: 7 days
Shore A Hardness	35±5
Adhesion in Peel (ASTM C-794)	Concrete: Meets ASTM C-920. Aluminum: Meets ASTM C-920. Glass: Meets ASTM C-920
Weathering Resistance	Excellent
Chemical Resistance	Good resistance to water, diluted acids, and diluted alkalines. Consult Technical Service for specific data.



PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://USA.SIKA.COM/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

Coverage		10.1 oz Cartridge: Yield in Linear feet			
		Depth	1/4"	3/8"	1/2"
Width	1/4"	24.3			
	3/8"	16.2	10.8		
	1/2"	12.1	8.1	6.1	
	3/4"	8.1	5.4	4.0	
	1"			3.0	
	1.25"			2.4	
	1.5"			2.0	

How to Use	
Surface Preparation	Clean all surfaces. Joint walls must be sound, clean, dry, frostfree, and free of oil and grease and any other contaminants. A roughened surface will also enhance bond. Install bond breaker tape or backer rod to prevent bond at base of joint.
Priming	Priming is not usually necessary. Most substrates only require priming if testing indicates a need or where sealant will be subjected to water immersion after cure. Consult Sikaflex Primer Technical Data Sheet or Technical Service for additional information on priming.
Application	Recommended application temperatures: 40°-100°F (4°-38°C). For cold weather application, condition units at approximately 70°F (21°C); remove prior to using. For best performance, Sikaflex Textured Sealant should be gunned into joint when joint slot is at mid-point of its designed expansion and contraction. Place nozzle of gun into bottom of the joint and fill entire joint. Keep the nozzle in the sealant, continue on with a steady flow of sealant preceding the nozzle to avoid air entrapment. Avoid overlapping of sealant to eliminate entrapment of air.
Tooling and Finishing	Tool sealant to ensure full contact with joint walls and remove air entrapment. Joint dimension should allow for 1/4 inch minimum and 1/2 inch maximum thickness for sealant. Proper design is 2:1 width to depth ratio.
Removal	Uncured material can be removed with approved solvent. Cured material can only be removed mechanically. For spillage, collect, absorb, and dispose of in accordance with current, applicable local, state, and federal regulations.
Limitations	<ul style="list-style-type: none"> ■ When over-coating with water, oil and rubber based paints, compatibility and adhesion testing is essential. ■ Sealant should be allowed to cure for 7 days prior to overcoating ■ Avoid exposure to high levels of chlorine. (Maximum continuous level is 5 ppm of chlorine.) ■ Maximum depth of sealant must not exceed 1/2 in.; minimum depth is 1/4 in. ■ Maximum expansion and contraction should not exceed 25% of average joint width. ■ Do not cure in the presence of curing silicone sealants. ■ Avoid contact with alcohol and other solvent cleaners during cure. ■ Do not apply when moisture-vapor-transmission condition exists from the substrate as this can cause bubbling within the sealant. ■ Use opened cartridges the same day. ■ When applying sealant, avoid air-entrapment. ■ Since system is moisture-cured, permit sufficient exposure to air. ■ White color tends to yellow slightly when exposed to ultraviolet rays. ■ Light colors can yellow slightly if exposed to direct gas fired heating elements prior to the formation of initial skin. ■ The ultimate performance of Sikaflex Textured Sealant depends on good joint design and proper application with joint surfaces properly prepared. ■ Do not tool with detergent or soap solutions. ■ Do not use in contact with bituminous/asphaltic materials.

PRIOR TO EACH USE OF ANY SIKA PRODUCT, THE USER MUST ALWAYS READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS ON THE PRODUCT'S MOST CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET WHICH ARE AVAILABLE ONLINE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING SIKA'S TECHNICAL SERVICE DEPARTMENT AT 800.933.7452 NOTHING CONTAINED IN ANY SIKA MATERIALS RELIEVES THE USER OF THE OBLIGATION TO READ AND FOLLOW THE WARNINGS AND INSTRUCTIONS FOR EACH SIKA PRODUCT AS SET FORTH IN THE CURRENT PRODUCT DATA SHEET, PRODUCT LABEL AND SAFETY DATA SHEET PRIOR TO PRODUCT USE.

KEEP CONTAINER TIGHTLY CLOSED. KEEP OUT OF REACH OF CHILDREN. NOT FOR INTERNAL CONSUMPTION. FOR INDUSTRIAL USE ONLY. FOR PROFESSIONAL USE ONLY.

For further information and advice regarding transportation, handling, storage and disposal of chemical products, users should refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety related data. Read the current actual Safety Data Sheet before using the product. In case of emergency, call CHEMTREC at 1-800-424-9300, International 703-527-3887.

Prior to each use of any Sika product, the user must always read and follow the warnings and instructions on the product's most current Product Data Sheet, product label and Safety Data Sheet which are available online at <http://usa.sika.com/> or by calling Sika's Technical Service Department at 800-933-7452. Nothing contained in any Sika materials relieves the user of the obligation to read and follow the warnings and instruction for each Sika product as set forth in the current Product Data Sheet, product label and Safety Data Sheet prior to product use.

SIKA warrants this product for one year from date of installation to be free from manufacturing defects and to meet the technical properties on the current Product Data Sheet if used as directed within shelf life. User determines suitability of product for intended use and assumes all risks. Buyer's sole remedy shall be limited to the purchase price or replacement of product exclusive of labor or cost of labor. NO OTHER WARRANTIES EXPRESS OR IMPLIED SHALL APPLY INCLUDING ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE. SIKA SHALL NOT BE LIABLE UNDER ANY LEGAL THEORY FOR SPECIAL OR CONSEQUENTIAL DAMAGES. SIKA SHALL NOT BE RESPONSIBLE FOR THE USE OF THIS PRODUCT IN A MANNER TO INFRINGE ON ANY PATENT OR ANY OTHER INTELLECTUAL PROPERTY RIGHTS HELD BY OTHERS. SALE OF SIKA PRODUCTS ARE SUBJECT SIKA'S TERMS AND CONDITIONS OF SALE AVAILABLE AT [HTTP://USA.SIKA.COM/](http://usa.sika.com/) OR BY CALLING 201-933-8800.

Visit our website at usa.sika.com

1-800-933-SIKA NATIONWIDE

Regional Information and Sales Centers. For the location of your nearest Sika sales office, contact your regional center.

Sika Corporation
201 Polito Avenue
Lyndhurst, NJ 07071
Phone: 800-933-7452
Fax: 201-933-6225

Sika Canada Inc.
601 Delmar Avenue
Pointe Claire
Quebec H9R 4A9
Phone: 514-697-2610
Fax: 514-694-2792

Sika Mexicana S.A. de C.V.
Carretera Libre Celaya Km. 8.5
Fracc. Industrial Balvanera
Corregidora, Queretaro
C. P. 76920
Phone: 52 442 2385800
Fax: 52 442 2250537



Sika and Sikaflex are registered trademarks.
Printed in Canada.

