

Product Description

TremGlaze® SA1100 is a pure siliconized acrylic latex sealant formulated to provide a fast-setting pliable seal with minimal shrinkage.

Basic Uses

TremGlaze SA1100 can be used for general purpose interior and exterior caulking where movement does not exceed 12.5%. Ideal for window frame perimeters.

Availability

Immediately available from your local Tremco Sales Representative, Tremco Distributor or Tremco Warehouse.

Packaging

10.1oz / 300 ml cartridge: Almond, Andersen Canvas, Andersen Sandstone, Andersen Terratone, Andersen White, Clear, White

Colors

See packaging for color availability by size. Special colors available upon request. Minimum order requirements exist for special colors.

Applicable Standards

- Conforms to ASTM C834
- CAN/CGSB 19-GP-17M

Limitations

- Do not apply to damp or contaminated surfaces.

Substrate Preparation

For good adhesion, the joint interface must be sound, clean and dry.

Depending on the substrate, or presence of form release agents, dust, masonry waterproofing's, loose mortar or laitance, architectural paints or finishes, the joint surface may require a thorough wire brushing, sandblasting and/or solvent washing.

Application

TremGlaze SA1100 is easy to apply with conventional caulking equipment. Fill joint completely and tool.

At 75 °F (23.9 °C), 50% RH, TremGlaze SA1100 can be painted over in 30 to 45 min with latex or oil-based paint.

Joint Design

May be used in any vertical or horizontal joint design in accordance with accepted architectural/engineering practice. Movement should not exceed 12.5% of the minimum joint width.

Joint Backing

Closed cell polyethylene backer rods are preferred as joint backing to control depth of sealant bead. Where depth of joint will prevent use of joint backing, an adhesive-backed polyethylene tape should be installed to prevent threeside adhesion. Joint backing must be dry at time of sealant application.

Sealant Dimensions

For joints 1/4" (6.4 mm) to 1/2" (12.7 mm) wide, the width-to-depth ratio should be equal. Joints 1/2" (12.7 mm) wide or greater should have a depth of 1/2" (12.7 mm).

Minimum joint size is 1/4" x 1/4" (6.4 mm x 6.4 mm).

Clean Up

Tooling is recommended immediately after application to ensure firm, intimate contact with the joint interface. Dry tooling is preferred. Cleaning can be accomplished with soapy water while sealant is in uncured state.

Warranty

Tremco warrants its Products to be free of defects in material but makes no warranty as to appearance or color. Since methods of application and on-site conditions are beyond our control and can affect performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Tremco Products. Tremco's sole obligation shall be, at its option, to replace or refund the purchase price of the quantity of Tremco Products proven to be defective, and Tremco shall not be liable for any loss or damage.

Please refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.

NOTE: All Tremco Safety Data Sheets (SDS) are in alignment with the Globally Harmonized System of Classification and Labelling of Chemicals (GHS) requirements.

TremGlaze® SA1100

Paintable Siliconized Acrylic Latex Sealant

TYPICAL PHYSICAL PROPERTIES

PROPERTY	TEST METHOD	TYPICAL VALUES
Extrudability	ASTM C834	6 g/s
Washout*	ASTM C834	None
Slump*	ASTM C834	None
Cracking*	ASTM C834	None
Discoloration*	ASTM C834	None
Adhesion Loss	ASTM C834	None
Volume Shrinkage	ASTM C834	25.9%
Low Temperature Flexibility	ASTM C834	None
Recovery	ASTM C834	93.7%
Slump	ASTM C834	2 mm
Stain Index	ASTM C834	0
Tack-Free Time	ASTM C834	15 min

*Artificial Weathering

0317/TGSA1100DS-STPlease refer to our website at www.tremcosealants.com for the most up-to-date Product Data Sheets.**Tremco Commercial Sealants & Waterproofing**

3735 Green Rd
Beachwood OH 44122
216.292.5000 / 800.321.7906

1451 Jacobson Ave
Ashland OH 44805
419.289.2050 / 800.321.6357

220 Wicksteed Ave
Toronto ON M4H1G7
416.421.3300 / 800.363.3213

1445 Rue de Coulomb
Boucherville QC J4B 7L8
514.521.9555