





# INDUSTRIAL PIPE & EQUIPMENT INSULATION ASTM C552 GRADE 6

FOAMGLAS® ONE™ insulation is a lightweight, rigid material composed of millions of completely sealed glass cells. It is manufactured by Owens Corning in a block form and then fabricated into a wide range of shapes and sizes to satisfy industrial and commercial insulation requirements.

#### **Features**

- Constant insulating efficiency
- Noncombustible
- Nonabsorbent
- · Impermeable to water and water vapor
- · Corrosion/chemical resistant
- Long-term dimensional stability
- · Vermin resistance
- · High compressive strength

## Standards, Code Compliance and Approvals<sup>1</sup>

FOAMGLAS® ONE™ Insulation can be certified to conform to the requirements of:

- ASTM C552 "Standard Specification for Cellular Glass Thermal Insulation" (Grade 6)
- ASTM C1639 "Standard Specification for Fabrication of Cellular Glass Piping and Tubing Insulation"
- Military Specification MIL-DLT-24244D (SH), with "Special Corrosion and Chloride Requirement"
- Nuclear Regulatory Guide 1.36, ASTM C795, C692, C871
- Flame Spread Index 0, Smoke Developed Index 0 (UL 723, ASTM E84), UL R2844; also classified by UL of Canada
- UL 1709, Rapid Rise Fire Tests of Protection Materials for Structural Steel
- UL Through Penetration Fire Stop Approved Systems
- UL 1479/ASTM E814; please search the UL database at www.ul.com
- Board of Steamship Inspection (Canada) Certificate of Approval No. 100/FI-98
- General Services Administration, PBS (PCD; 15250, Public Building Services Guide Specification, "Thermal Insulation (Mechanical)")
- GreenSpec® listed, www.greenspec.com
- EC-114.456 USCG 164.109/EC0736/114.456
  Approval for Marine Use
- FOAMGLAS® ONE™ Insulation is identified by Federal Supply Code for Manufacturers (FSCM 08869)
- 1 Request for certification shall be included with valid order for FOAMGLAS® ONE™ Insulation.

## **Applications**

- · Cryogenic systems
- · Low-temperature pipe, equipment, tanks and vessels
- · Medium- and high-temperature pipes and equipment
- · Hot oil and hot asphalt storage tanks
- Heat transfer fluid systems
- Hydrocarbon processing systems
- · Chemical processing systems
- Steam and chilled water piping
- · Commercial piping and ductwork
- · Direct burial/underground

## FOAMGLAS® ONE™ BLOCK DIMENSIONS

	STANDARD FORM	LARGE FORMAT				
	SI	ENGLISH	ENGLISH			
WIDTH & LENGTH	450 x 600 mm	18 x 24 in	18 x 36 in			
THICKNESS	40-180 mm (10 mm increments)	1.5-7 in (½ in increments)	3-8 in (½ in increments)			

Contact a representative for regional availability.

## Physical and Thermal Properties<sup>2,3</sup>

PROPERTY	ASTM METHOD	SI	ENGLISH					
Absorption of Moisture	C240	< 0.2% by Vol	< 0.2% by Vol					
Capillarity	_	None						
Chemical Resistance	_	Impervious to common acids and their fumes						
Coefficient of Linear Thermal Expansion	F000	25 to 300°C, 9.0 x 10 <sup>-6</sup> /K	75 to 575°F, 5.0 x 10 <sup>-6</sup> /°F					
	E228	-170 to 25°C, 6.6 x 10 <sup>-6</sup> /K	-274 to 75°F, 3.7 x 10 <sup>-6</sup> /°F					
Combustibility	E136	Noncombustible						
Composition	_	Soda-lime glass. Inorganic. No	fibers or binders.					
Compressive Strength	0165/0040/0550	AVG = 620 kPa	AVG = 90 lb/in <sup>2</sup>					
	C165/C240/C552	LSL = 414 kPa	LSL = 60 lb/in <sup>2</sup>					
Corrosion, Water Soluble Ions, and pH	C871 C692 C1617	Acceptable for use with stainles Pass < DI Water	ss steel					
Density (±10%)	C303	115 kg/m³	7.18 lb/ft³					
Dimensional Stability	-	Excellent — does not shrink or s	swell					
Flexural Strength	0000/0040	AVG = 480 kPa	AVG = 70 lb/in <sup>2</sup>					
	C203/C240	LSL = 283 kPa	LSL = 41 lb/in <sup>2</sup>					
Hygroscopicity	_	No increase in weight at 90% re	elative humidity					
Modulus of Elasticity, Approximate (v = 0.25)	C623	900 MPa	1.3 x 10 <sup>5</sup> lb·in <sup>-2</sup>					
Service Temperature	_	-268 to 482°C	-450 to 900°F					
Specific Heat	E1461	0.77 kJ/kg·K @ 25°C	0.18 BTU/lb°F @ 77°F					
Surface Burning Characteristics	E84	Flame Spread Index 0/Smoke D	Development Index 0					
Water Vapor Permeability	E96 Wet Cup	0.00 ng/Pa·s·m	0.00 perm·inch					

## Thermal Conductivity (λ) Values at Select Mean Temperatures (ASTM C518, C177)

TEMPERATURE	°C (°F)	204 (400)	149 (300)	93 (200)	38 (100)	24 (75)	10 (50)	-18 (0)	-46 (-50)	-73 (-100)	-101 (-150)	-129 (-200)	-157 (-250)	-165 (-265)
ASTM C552 <sup>3</sup>	W/m K (BTU in/hr °F ft²)	0.084 (0.58)	0.069 (0.48)	0.058 (0.40)	0.048 (0.33)	0.045 (0.31)	0.043 (0.30)	0.039 (0.27)	0.035 (0.24)	0.030 (0.21)	0.027 (0.19)	0.025 (0.17)	0.023 (0.16)	N/A
FOAMGLAS® ONE™ INSULATION⁴	W/m K (BTU in/hr °F ft²)	0.078 (0.54)	0.066 (0.46)	0.054 (0.38)	0.044 (0.31)	0.042 (0.29)	0.040 (0.28)	0.036 (0.25)	0.032 (0.22)	0.029 (0.20)	0.026 (0.18)	0.023 (0.16)	0.021 (0.14)	0.020 (0.14)

- 2 Values represent typical physical and thermal properties.
- 3 Type 1 Block (Grade 6) limit values, where applicable, are specified by ASTM C552 Standard Specification for Cellular Glass Thermal Insulation.
- 4 The values were determined by evaluating a polynomial at the insulation mean temperature. Contact Owens Corning for assistance applying our design polynomials to your application.

For additional information on FOAMGLAS® ONE™ insulation or systems, please contact Owens Corning at any of our worldwide offices or visit us at www.foamglas.com. The information contained herein is accurate and reliable to the best of our knowledge. But, because Pittsburgh Corning, LLC has no control over installation workmanship, accessory materials or conditions of application, NO EXPRESSED OR IMPLIED WARRANTY OF ANY KIND, INCLUDING THOSE OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR PURPOSE, IS MADE as to the performance of an installation containing Owens Corning products. In no event shall Pittsburgh Corning, LLC be liable for any damages arising because of product failure, whether incidental, special, consequential or punitive, regardless of the theory of liability upon which any such damages are claimed. Pittsburgh Corning, LLC provides written warranties for many of its products, and such warranties take precedence over the statements contained herein.

# Industrial & Commercial Sales

**Americas** +1 800 327 6126

Asia-Pacific

Singapore: +65 9635 9184 China: +86 (0) 21 6101 7179 Japan: +81 3 6365 4307

Europe, Middle East & Africa +32 13 661 721

### **Technical Services**

Americas & Asia-Pacific +1 800 327 6126 foamglastechnical@owenscorning.com

> Europe, Middle East & Africa +32 13 611 468 Industrytechnical@foamglas.com



PITTSBURGH CORNING, LLC

ONE OWENS CORNING PARKWAY TOLEDO, OHIO 43659 USA

Toll Free + 1 800 327 6126

For web-based Sales and Technical Service inquiries, please visit **www.foamglas.com**