



AKOUSTI-LINER™ R

Temperature Limit: 250° F (121° C)

DESCRIPTION

Akousti-Liner R insulation is a heavy density fiberglass board insulation product made from inorganic glass fibers bonded by a thermosetting binder. Its base board is brown with a black mat facing on the airstream surface. Airstream surface mat facing is treated with an EPA-registered anti-microbial agent to aid in the prevention of fungal and bacterial growth.

SUSTAINABILITY

Manson Insulation products with ECOSE® Technology are made using our patented, bio-based binder - a smarter alternative to the phenol/formaldehyde (PF) binder traditionally used in fiberglass products. The bio-based binder holds our product together and gives the product its unique appearance.

Akousti-Liner R is formaldehyde-free and made from sustainable resources, such as recycled glass and sand. And we're proud to be putting glass bottles back to work rather than into landfills. Our products are made with a minimum of 50% recycled glass—totaling an average of 26 million bottles each month.

APPLICATION

Manson Insulation Akousti-Liner R insulation is a premium, extra durable rigid liner for use on flat duct surfaces. Some typical applications include fan plenums and air distribution ducting on industrial and commercial heating, ventilating and air-conditioning systems.

INSTALLATION

All duct liner shall be installed in accordance with the requirement of the NAIMA Fibrous Glass Duct Liner Standard or SMACNA HVAC Duct Construction Standard and the project specification. Liner shall be adhered with adhesive (complying with ASTM C916) and mechanical fasteners.

LIMITATION

Duct liner should be kept clean and dry during shipping, storage, installation and system operation. When condensation is permitted to occur between nested liner and galvanized steel panels, discoloration of the metal may occur.

SPECIFICATION COMPLIANCE

- ASTM C1071; Type II
- NFPA 90A and NFPA 90B
- UL/ULC Classified FHC 25/50
- ASHRAE 62

INDOOR AIR QUALITY

- **Asthma & Allergy Friendly®**
- Verified Healthier Air™
- UL Environment
 - GREENGUARD Certified
 - GREENGUARD Gold Certified
 - Validated to be Formaldehyde-Free
- Does not contain polybrominated diphenyl ethers (PBDE) such as Penta-BDE, Octa-BDE, or Deca-BDE
- EUCEB Certified

AKOUSTI-LINER™ R

Temperature Limit: 250° F (121° C)

FIBERGLASS AND MOLD

Fiberglass insulation will not sustain mold growth. However, mold can grow on almost any material when it becomes wet and contaminated. Carefully inspect any insulation that has been exposed to water. If it shows any sign of mold, it must be discarded. If the material is wet but shows no evidence of mold, it should be dried rapidly and thoroughly. If it shows signs of facing degradation from wetting, it should be replaced. Air handling insulation used in the air stream must be discarded if exposed to water.


NOTES

The chemical and physical properties of this product represent average values determined in accordance with accepted test methods. The data is subject to normal manufacturing variations. The data is supplied as a technical service and is subject to change without notice. References to numerical flame spread ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions.

Check with your Manson Insulation Area Manager to ensure information is current.

MECHANICAL FASTENER LOCATION

VELOCITY/FT./MIN. (M/SEC.)	0-255 (0-12.7)	2501-5000 (12.7-25.4)
A. From corners of duct	4" (102 mm)	4" (102 mm)
B. From transverse of duct	3" (76 mm)	3" (76 mm)
C. Across width of duct, on centers (min. 1/side)	12" (305 mm)	6" (152 mm)
D. Across length of duct, on centers (min. 1/side)	18" (457 mm)	16" (406 mm)



TECHNICAL DATA

PROPERTY (UNIT)	TEST	PERFORMANCE
Corrosiveness	ASTM C665	Does not accelerate corrosion of steel
Corrosion	ASMT C1617	Pass
Maximum Service Temperature	ASTM C411	250° F (121° C)
Maximum Air Velocity	ASTM C1071, UL 181 Erosion Test	Max. 5,000 ft./min. (25.4 m/sec.)
Water Vapor Sorption (by weight)	ASTM C1104	Less than 3%
Microbial Growth	ASTM C1338, ASTM G21, ASTM G22	Pass
Surface Burning Characteristics (flame spread/smoke developed)	ASTM E84, UL 723, CAN/ULC S102	UL/ULC Classified FHC 25/50

*Tested at 12,500 ft/ min per UL 181 - 2.5 times certified velocity rating

FORMS AVAILABLE

THICKNESS	DENSITY	WIDTH	LENGTH
1" (25 mm)	3 PCF (48 kg/m3)	24" (610 mm), 48" (1,219 mm)	48" (1,219 mm), 96" (2,438 mm), 120" (3,048 mm)
1.5" (38 mm)			
2" (52 mm)			

AKOUSTI-LINER™ R

Temperature Limit: 250° F (121° C)

ACOUSTICAL PERFORMANCE | ASTM C423, TYPE A MOUNTING

DENSITY	THICKNESS	FREQUENCY (Hz)						
		125	250	500	1000	2000	4000	NRC
3.0 PCF (48 kg/m³)	1" (25 mm)	0.13	0.24	0.56	0.83	0.92	0.98	0.65
	1½" (38 mm)	0.19	0.41	0.89	1.02	1.03	1.04	0.85
	2" (51 mm)	0.33	0.67	1.07	1.07	1.03	1.06	0.95

NOTE: ASHRAE Handbook for HVAC Applications – Sound and Vibration Control contains insertion loss values for lined sheet metal ducts.

THERMAL PERFORMANCE | ASTM C177


MEAN TEMPERATURE 75° F (24° C)

DENSITY	THICKNESS	C-VALUE ¹		R-VALUE ²	
		BTU/ FT² · HR · °F	W/ M² · °C	FT² · HR · °F/ BTU	M² · °C/ W
3.0 PCF (48 kg/m³)	1" (25 mm)	0.23	1.31	4.3	0.76
	1½" (38 mm)	0.15	0.85	6.5	1.15
	2" (51 mm)	0.11	0.62	8.7	1.53

¹The lower the value, the better the performance.

²The higher the value, the better the performance.

FRICTION LOSS (INCHES OF WATER PER 100')



FT./MIN.	HYDRAULIC DIAMETER						
VELOCITY	10"	16"	24"	32"	40"	72"	100"
500	0.056	0.031	0.018	0.013	0.010	0.005	0.003
600	0.080	0.044	0.026	0.018	0.014	0.007	0.004
700	0.108	0.059	0.035	0.025	0.019	0.009	0.006
800	0.140	0.077	0.046	0.032	0.024	0.012	0.008
900	0.176	0.096	0.058	0.040	0.031	0.015	0.010
1000	0.216	0.118	0.071	0.050	0.038	0.018	0.012
2000	0.845	0.463	0.278	0.194	0.147	0.071	0.048
3000	1.887	1.034	0.620	0.432	0.328	0.159	0.106
4000	3.340	1.831	1.097	0.765	0.580	0.281	0.188
5000	5.206	2.854	1.710	1.193	0.904	0.438	0.293

